

Sheet1

Yew bows									
Origin of wood	RPI	Weight [g]	Profile	Length ntn [mm]	Width [mm]	Depth [mm]	Draw length [i	Draw weight [l	Draw weight 30" [lb]
1 SK	50	890	O	1942	37.8	33.3	30	105	105
2 SK	40-100+	1164	SS	2014	42	36.3	30	135	135
3 SK	30	1058	D	1963	39.1	34.1	30	90	90
4 SK	40	904	RD	2012	38	32.9	30	95	95
5 SK	50	925	O	2067	37.1	34.5	32	125	117.1875
6 IT	25	1134	RD	1940	38.4	34	30	100	100
7 IT	30-40	943	D	2032	34.9	33	32	85	79.6875
8 IT	30-60	1000	D	1976	37.8	34.7	30	130	130
9 IT	30	885	D	1911	33.7	31.5	29	108	111.7241379
10 IT	30-40	1134+g (brok	D	2089	40.7	34.7	32	133	124.6875
11 IT	20-60	1075	D	2074	40.5	35.8	32	100	93.75
12									
13									
14									
15									
16									
17									
18									
19									
20									
Average	37.5	997.8		2001.8	38.2	34.1	30.6	109.6	107.5
MR av. bow				1925.0	35.8	33.1	30.0		103.9
							28.0		96.9
Average SK		988.2		1999.6	38.8	34.2	30.4	110.0	108.4
Average IT		1007.4		2003.7	37.7	34.0	30.8	109.3	106.6
									101.5
									105.9